

## 消泡剂

### 产品介绍

Defom 3150 为适用于溶剂型或无溶剂型涂料中的消泡剂，特别是不饱和聚酯底漆体系的抑泡与脱泡。

### 产品特征

组成	破泡聚合物，不含硅酮
外观	澄清液体
不挥发份	40 - 43%
溶剂	芳香族碳氢溶剂
比重	约 0.88

### 应用领域

- 不饱和聚酯
- 溶剂型涂料
- 无溶剂涂料

### 主要特性

- 在无溶剂或高粘度体系中，因机械力量混入的气泡不易脱除，Defom 3150 能在初期即抑制气泡混入，并同时帮助涂膜之气泡逸离与脱除。
- 帮助多孔性底材涂装时的脱泡。
- 对含硬脂酸锌不饱和聚酯底漆的抑泡与脱泡效果佳。
- 对不饱和聚酯树脂有较佳的相容性。

### 使用方法

- 可在任何阶段添加。
- 研磨前添加，可得最佳效果。
- 请试验最适添加量。。

### 添加量

对全量添加 0.1 - 0.5%。

### 操作与安全

本产品含有溶剂，须小心操作，避免接触皮肤与眼睛，其他资料请参考物质安全资料表。

### 储存条件

- 远离热及火源。
- 置于阴凉通风处，容器保持紧密。
- 储存环境为 0°C 至 40°C。

### 包装

净重：25 kg

*NOTE: The information herein is currently believed to be accurate. We do not guarantee its accuracy. Purchasers shall not rely on statements herein when purchasing any products. Purchasers should make their own investigations to determine if such products are suitable for a particular use. The products discussed are sold without warranty, express or implied, including a warranty of merchantability and fitness for use. Purchasers will be subject to a separate agreement which will not incorporate this document.*

*© Copyright 2006, Elementis Specialties, Inc. All rights reserved. Copying and/or downloading of this document or information therein for republication is not allowed unless prior written agreement is obtained from Elementis Specialties, Inc.*

*® Trademark of Elementis Specialties, Inc.*

[www.elementis-specialties-asia.com](http://www.elementis-specialties-asia.com)

B01 Nov-09

## 有效期

Defom 3150 自生产日起，保质期限为 18 个月。

## 品质保证

本公司自 1992 年起获得 ISO 9001/9002 质量体系认证，确保所有操作符合标准规定。

---

### 海名斯特殊化学，亚洲

#### Head Office

上海市松江工业区联阳路 99 号  
邮编 201613  
99, Lianyang Road, Songjiang  
Industrial Zone, Shanghai,  
China 201613  
Tel.: +86 21 57740348  
Fax.: +86 21 57743563

#### Taiwan

新竹县湖口乡新竹工业区光复北路  
92 号  
92, Kuang-Fu North Road, Hsinchu  
Industrial Park, Hukou,  
Hsinchu, Taiwan  
Tel.: +886 3 5984035  
Fax.: +886 3 5983301

#### Malaysia

Lot PT 55, 64 & 65,  
Jalan Hulu Tinggi 26/6, Seksyen 26,  
40400 Shah Alam Selangor Darul  
Ehsan, Malaysia  
Tel.: +603 5191 9979  
Fax.: +603 5191 6811

#### Japan

15-14 Minaminisemba 1-Chome  
Chou-Ku, Osaka  
542-0081 Japan  
Tel.: +81 6 6267 6210  
Fax.: +81 6 6267 6213